

Ronfalin 100 G10
Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

Product Description
10% glass fibre reinforced ABS for injection moulding of parts in structural applications. Used in Automotives and domestic appliances

General

Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.09 g/cm³	1.09 g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
220°c/10.0 Kg	20 g/10 min	20 g/10 min	
230°c/5.0 Kg	11 g/10 min	11 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	7980 psi	55.0 MPa	ISO 527-2
Tensile Strain (Break)	15 %	15 %	ISO 527-2
Flexural Modulus	500000 psi	3450 MPa	ISO 178
Flexural Stress	12000 psi	83.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength	3.3 ft·lb/in²	7.0 kJ/m²	ISO 180
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	203 °F	95.0 °C	ISO 306/B50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.13 In (3.2 Mm))	HB	HB	UL 94

Notes
These are typical property values not to be construed as specification limits.

