

RONFALIN[®] ABS 1237

Acrylonitrile Butadiene Styrene
Engineering Plastics

Product Description

High flow, general purpose ABS Compound.

General

Features	• Good Flow • UV Stabilized
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• ABS

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm ³	1.04 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	36 cm ³ /10min	36 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	377000 psi	2600 MPa	ISO 527-2/1A/1
Tensile Stress			ISO 527-2/1A/50
Yield	6960 psi	48.0 MPa	
Break	5370 psi	37.0 MPa	
Tensile Strain (Yield)	3.0 %	3.0 %	ISO 527-2/1A/50
Nominal Tensile Strain at Break	16 %	16 %	ISO 527-2/1A/50
Flexural Modulus ¹	406000 psi	2800 MPa	ISO 178
Flexural Stress ¹ (4.8% Strain)	11500 psi	79.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.8 ft·lb/in ²	8.0 kJ/m ²	
73°F (23°C)	8.6 ft·lb/in ²	18 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	39 ft·lb/in ²	83 kJ/m ²	
73°F (23°C)	No Break	No Break	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	17400 psi	120 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	196 °F	91.0 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	174 °F	79.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	217 °F	103 °C	ISO 306/A50
--	203 °F	95.0 °C	ISO 306/B50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+14 ohms	1.0E+14 ohms	IEC 60093
Volume Resistivity	1.0E+14 ohms·m	1.0E+14 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112





RONFALIN® ABS 1237

Acrylonitrile Butadiene Styrene
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.6 mm)	HB	HB	
0.13 in (3.2 mm)	HB	HB	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1290 °F	700 °C	
0.12 in (3.0 mm)	1290 °F	700 °C	

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications



RONFALIN® ABS 1237

Acrylonitrile Butadiene Styrene
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Regrind	30 %	30 %
Processing (Melt) Temp	446 to 482 °F	230 to 250 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

