

Ronfalin ABS 1412 GF 17

Acrylonitrile Butadiene Styrene

LyondellBasell Industries

Engineering Plastics

Product Description

17% glass fiber reinforced ABS compound. (Former name: POLYMAN FABS 17GF)

General

Filler / Reinforcement	• Glass Fiber, 17% Filler by Weight
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.16 g/cm ³	1.16 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 Kg)	12 cm ³ /10min	12 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	783000 psi	5400 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	10600 psi	73.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	1.9 %	1.9 %	ISO 527-2/5
Flexural Modulus ¹	856000 psi	5900 MPa	ISO 178
Flexural Stress			ISO 178
2.2% Strain ¹	16200 psi	112 MPa	
2.3% Strain ^{2, 3}	14500 psi	100 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	2.9 ft·lb/in ²	6.0 kJ/m ²	
73°F (23°C)	3.3 ft·lb/in ²	7.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	10 ft·lb/in ²	22 kJ/m ²	
73°F (23°C)	10 ft·lb/in ²	22 kJ/m ²	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	19900 psi	137 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	216 °F	102 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	203 °F	95.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	216 °F	102 °C	ISO 306/B50
--	225 °F	107 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112





Ronfalin ABS 1412 GF 17

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1290 °F	700 °C	

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications



Ronfalin ABS 1412 GF 17

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	446 to 500 °F	230 to 260 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

Notes

- ¹ 0.079 in/min (2.0 mm/min)
- ² 0.091 in/min (2.3 mm/min)
- ³ at Break

Notes

These are typical property values not to be construed as specification limits.

