

# CYCOLAC<sup>TM</sup> RESIN INP984

REGION AMERICAS

## DESCRIPTION

SABIC INP 984 is a 45% polybutyl acrylate rubber grafted weatherable ASA modifier resin. Provides excellent impact, heat distortion and weatherability properties. Maintains polymer properties in UV and thermal environments. Toughens compatible rigid polymers without additional impact modification. Expands the use temperature window of compounds. Offers compatibility with many polar polymers. Improve UV resistance when blended with less stable polymers. SABIC INP984 is well suited to produce good weatherability in rigid polymer applications. Can be effectively alloyed with PVC and other miscible thermoplastics in molded, extruded or calendered applications to provide improved heat distortion

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Hardness, Shore D	65	-	ASTM D 2240
<b>PHYSICAL</b>			
Specific Gravity	1.06	-	ASTM D 792
Density (Molded)	1.07	g/cm <sup>3</sup>	ISO 1183
Mean Resin Particle Size	465	micrometer	SABIC method
Total NA Volatiles	0.1	%	SABIC method
Rubber	45	%	SABIC method
Bulk Density	0.26	g/cm <sup>3</sup>	ASTM D 1895

