



## LNP™ THERMOCOMP™ Compound 2X98703

### Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound PDX-FP-E-98703

Product reorder name: 2X98703

LNP THERMOCOMP 2X98703 is a compound based on ETFE Copolymer resin containint Proprietary Filler(s).

| TYPICAL PROPERTIES <sup>1</sup>              | TYPICAL VALUE | Unit                | Standard    |
|----------------------------------------------|---------------|---------------------|-------------|
| <b>MECHANICAL</b>                            |               |                     |             |
| Tensile Stress, yld, Type I, 5 mm/min        | 1020          | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Stress, brk, Type I, 5 mm/min        | 990           | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Strain, yld, Type I, 5 mm/min        | 5.6           | %                   | ASTM D 638  |
| Tensile Strain, brk, Type I, 5 mm/min        | 5.9           | %                   | ASTM D 638  |
| Tensile Modulus, 5 mm/min                    | 144500        | kgf/cm <sup>2</sup> | ASTM D 638  |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 1450          | kgf/cm <sup>2</sup> | ASTM D 790  |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 108000        | kgf/cm <sup>2</sup> | ASTM D 790  |
| Tensile Stress, yield, 5 mm/min              | 95            | MPa                 | ISO 527     |
| Tensile Stress, break, 5 mm/min              | 88            | MPa                 | ISO 527     |
| Tensile Strain, yield, 5 mm/min              | 5             | %                   | ISO 527     |
| Tensile Strain, break, 5 mm/min              | 5.5           | %                   | ISO 527     |
| Tensile Modulus, 1 mm/min                    | 11220         | MPa                 | ISO 527     |
| Flexural Stress, yield, 2 mm/min             | 135           | MPa                 | ISO 178     |
| Flexural Modulus, 2 mm/min                   | 10440         | MPa                 | ISO 178     |
| <b>IMPACT</b>                                |               |                     |             |
| Izod Impact, unnotched, 23°C                 | 49            | cm-kgf/cm           | ASTM D 4812 |
| Izod Impact, notched, 23°C                   | 41            | cm-kgf/cm           | ASTM D 256  |
| Multiaxial Impact                            | 81            | cm-kgf              | ISO 6603    |
| Instrumented Impact Total Energy, 23°C       | 203           | cm-kgf              | ASTM D 3763 |
| Izod Impact, unnotched 80*10*4 +23°C         | 88            | kJ/m <sup>2</sup>   | ISO 180/1U  |
| Izod Impact, notched 80*10*4 +23°C           | 34            | kJ/m <sup>2</sup>   | ISO 180/1A  |
| <b>THERMAL</b>                               |               |                     |             |
| HDT, 0.45 MPa, 3.2 mm, unannealed            | 248           | °C                  | ASTM D 648  |





## LNP™ THERMOCOMP™ Compound 2X98703

Americas: COMMERCIAL

| TYPICAL PROPERTIES <sup>1</sup>        | TYPICAL VALUE | Unit              | Standard   |
|----------------------------------------|---------------|-------------------|------------|
| <b>THERMAL</b>                         |               |                   |            |
| HDT, 1.82 MPa, 3.2mm, unannealed       | 214           | °C                | ASTM D 648 |
| CTE, -40°C to 40°C, flow               | 1.7E-05       | 1/°C              | ASTM E 831 |
| CTE, -40°C to 40°C, xflow              | 7.2E-05       | 1/°C              | ASTM E 831 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 239           | °C                | ISO 75/Bf  |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm  | 187           | °C                | ISO 75/Af  |
| <b>PHYSICAL</b>                        |               |                   |            |
| Specific Gravity                       | 1.73          | -                 | ASTM D 792 |
| Density                                | 1.73          | g/cm <sup>3</sup> | ASTM D 792 |
| Moisture Absorption, 50% RH, 24 hrs    | 0.01          | %                 | ASTM D 570 |
| Mold Shrinkage, flow, 24 hrs (5)       | 0.4           | %                 | ASTM D 955 |
| Mold Shrinkage, xflow, 24 hrs (5)      | 1             | %                 | ASTM D 955 |
| Moisture Absorption (23°C / 50% RH)    | 0.01          | %                 | ISO 62     |





## LNP™ THERMOCOMP™ Compound 2X98703

Americas: COMMERCIAL

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 120 - 150     | °C   |
| Drying Time                 | 4             | hrs  |
| Melt Temperature            | 315           | °C   |
| Front - Zone 3 Temperature  | 325 - 340     | °C   |
| Middle - Zone 2 Temperature | 300 - 325     | °C   |
| Rear - Zone 1 Temperature   | 280 - 300     | °C   |
| Mold Temperature            | 90 - 120      | °C   |
| Back Pressure               | 0.2 - 0.3     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |

