

CYCOLOY™ FR RESINS CM6220

REGION ASIA

DESCRIPTION

CYCOLOY CM6220 resin is a mineral filled modified PC blend featuring of high modulus (6GPa), good flow and ductility, low warpage. It is of non-Br & non-Cl flame retardant systems intended to meet thin wall flame resistance and various environmental requirements.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	55	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	34	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	15	%	ASTM D638
Tensile Modulus, 5 mm/min	5850	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	98	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	6030	MPa	ASTM D790
Hardness, Rockwell R	109	-	ASTM D785
Tensile Stress, yield, 5 mm/min	56	MPa	ISO 527
Tensile Stress, break, 5 mm/min	30	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	6	%	ISO 527
Tensile Modulus, 1 mm/min	5570	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	98	MPa	ISO 178
Flexural Modulus, 2 mm/min	6150	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	95	J/m	ASTM D256
Izod Impact, notched, -30°C	52	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	30	J	ASTM D3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	98	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	92	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	85	°C	ASTM D648
CTE, 23°C to 80°C, flow	3.4E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.2E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	87	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.39	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.3	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	12	g/10 min	ASTM D1238
Density	1.4	g/cm³	ISO 1183
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating	0.8	mm	UL 94



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	85 – 95	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	16	Hrs	
Melt Temperature	255 – 285	°C	
Nozzle Temperature	255 – 285	°C	
Front - Zone 3 Temperature	255 – 285	°C	
Middle - Zone 2 Temperature	255 – 285	°C	
Rear - Zone 1 Temperature	245 – 280	°C	
Mold Temperature	70 – 90	°C	

