

Cycoloy* Resin C2950

Americas: COMMERCIAL

Non-chlorinated and non-brominated flame retardant PC/ABS offering balanced flow and impact plus improved heat resistance intended for various applications.

You may also be interested in:		
Enhanced Property	Data Sheet	
Improved Flow/Impact Balance	CX7211	Additional Information
Improved Flow/Impact Balance	CX7110	Additional Information
Improved UL Performance	CX7240	Additional Information

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	40	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	102	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2650	MPa	ASTM D 790
Hardness, Rockwell R	123	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	534	J/m	ASTM D 256
Izod Impact, notched, -30°C	160	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	54	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	112	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	90	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	104	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	95	°C	ASTM D 648
CTE, -30°C to 30°C, flow	7.2E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.2E-05	1/°C	ASTM D 696
Thermal Conductivity	0.2	W/m-°C	ASTM C 177
Relative Temp Index, Elec	85	°C	UL 746B
Relative Temp Index, Mech w/impact	85	°C	UL 746B



Cycoloy* Resin C2950

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
Relative Temp Index, Mech w/o impact	85	°C	UL 746B
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Specific Gravity, color	1.22	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.4	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.4 - 0.6	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm	0.4 - 0.6	%	SABIC Method
Melt Flow Rate, 260°C/2.16 kgf	10	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	1.E+17	Ohm-cm	ASTM D 257
Surface Resistivity	>1.E+16	Ohm	ASTM D 257
Dielectric Strength, in oil, 3.2 mm	19.4	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3	-	ASTM D 150
Relative Permittivity, 100 Hz	3	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.005	-	ASTM D 150
Dissipation Factor, 100 Hz	0.0049	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.49	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2.48	mm	UL 94
CSA (See File for complete listing)	LS88480	File No.	CSA LISTED



Cycloloy* Resin C2950

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
FLAME CHARACTERISTICS Oxygen Index (LOI)	32	%	ASTM D 2863



Cycoloy* Resin C2950

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	80 - 90	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	245 - 275	°C
Nozzle Temperature	245 - 275	°C
Front - Zone 3 Temperature	245 - 275	°C
Middle - Zone 2 Temperature	220 - 275	°C
Rear - Zone 1 Temperature	220 - 255	°C
Mold Temperature	60 - 80	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	30 - 80	%
Vent Depth	0.038 - 0.076	mm

• NOTE: Back Pressure, Screw Speed, Shot to Cylinder Size and Vent Depth are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

