



LNP™ FARADEX™ Compound NS003

Americas: COMMERCIAL

Also known as: LNP™ FARADEX™ Compound PCA-S-1003

Product reorder name: NS003

LNP FARADEX NS003 is a compound based on PC+ABS resin containing 15% Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	530	kgf/cm ²	ASTM D 638
Tensile Stress, break	500	kgf/cm ²	ASTM D 638
Tensile Strain, yield	3.3	%	ASTM D 638
Tensile Strain, break	4.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	31700	kgf/cm ²	ASTM D 638
Flexural Stress	910	kgf/cm ²	ASTM D 790
Flexural Modulus	30500	kgf/cm ²	ASTM D 790
Tensile Stress, yield	50	MPa	ISO 527
Tensile Stress, break	46	MPa	ISO 527
Tensile Strain, yield	3.5	%	ISO 527
Tensile Strain, break	6	%	ISO 527
Tensile Modulus, 1 mm/min	2700	MPa	ISO 527
Flexural Stress	86	MPa	ISO 178
Flexural Modulus	2800	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	58	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	152	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	32	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	120	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D 648





LNP™ FARADEX™ Compound NS003

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	7.74E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	5.9E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	115	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75/Af
PHYSICAL			
Density	1.24	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.35	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.3	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.35	%	ISO 294
Density	1.21	g/cm ³	ISO 1183
ELECTRICAL			
Volume Resistivity	1.E+04	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+01 - 1.E+03	Ohm	ASTM D 257
Shielding Effectiveness @ 3mm	50 - 65	dB	SABIC Method





LNP™ FARADEX™ Compound NS003

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	220 - 260	°C
Front - Zone 3 Temperature	245 - 255	°C
Middle - Zone 2 Temperature	230 - 245	°C
Rear - Zone 1 Temperature	220 - 230	°C
Mold Temperature	40 - 80	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

