



CYCOLOY® LG8002
Americas: **COMMERCIAL**

Automotive. Low gloss, high impact and ductility at 73F and -22F. UV-stable colors.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	85	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2280	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	641	J/m	ASTM D 256
Izod Impact, notched, -30°C	587	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	47	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	41	J	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	121	°C	ASTM D 648
HDT, 1.84 MPa, 3.2mm, unannealed	104	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E 831
Thermal Conductivity	0.25	W/m-°C	ASTM C 177
PHYSICAL			
Specific Gravity	1.13	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.7	%	GE Method
Melt Flow Rate, 260°C/5.0 kgf	6.5	g/10 min	ASTM D 1238
OPTICAL			
Gloss, untextured, 60 degrees	30	-	ASTM D 523





CYCOLOY® LG8002
Americas: *COMMERCIAL*

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	105 - 110	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	275 - 300	°C
Nozzle Temperature	275 - 300	°C
Front - Zone 3 Temperature	260 - 300	°C
Middle - Zone 2 Temperature	255 - 295	°C
Rear - Zone 1 Temperature	250 - 290	°C
Mold Temperature	60 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	30 - 80	%
Vent Depth	0.038 - 0.076	mm

