

Xenoy* Resin ECX1410

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yield	78	MPa	SABIC - Japan Method
Tensile Strain, break	12 - 12	%	SABIC - Japan Method
Flexural Stress	125	MPa	ASTM D 790
Flexural Modulus	3830	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	33	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.3	-	ASTM D 792

