

Xenoy* Resin X6320

Americas: COMMERCIAL

X6320 is a mineral filled PBT/PC resin developed for automotive painted doorhandles. Key advantages are excellent surface finish, easy processing and paint quality.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	63	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	41	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	55.8	%	ASTM D 638
Tensile Modulus, 5 mm/min	3890	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	107	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3550	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	63	MPa	ISO 527
Tensile Stress, break, 5 mm/min	43	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.3	%	ISO 527
Tensile Strain, break, 5 mm/min	25.4	%	ISO 527
Tensile Modulus, 1 mm/min	3860	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	106	MPa	ISO 178
Flexural Modulus, 2 mm/min	3540	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	45	J/m	ASTM D 256
Izod Impact, notched, -30°C	45	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	65	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m ²	ISO 179/1eA



Xenoy* Resin X6320

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
Vicat Softening Temp, Rate B/50	139	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	121	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	88	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
CTE, -40°C to 60°C, flow	6.15E-05	1/°C	ASTM E 831
CTE, -40°C to 60°C, xflow	7.02E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	5.99E-03	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.84E-03	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	78	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.33	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.8	%	SABIC Method
Melt Flow Rate, 250°C/5.0 kgf	20	g/10 min	ASTM D 1238
Density	1.33	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	16	cm³/10 min	ISO 1133



Xenoy* Resin X6320

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	110	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260 - 275	°C
Nozzle Temperature	255 - 270	°C
Front - Zone 3 Temperature	255 - 275	°C
Middle - Zone 2 Temperature	250 - 270	°C
Rear - Zone 1 Temperature	245 - 265	°C
Mold Temperature	65 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 80	rpm
Shot to Cylinder Size	50 - 80	%
Vent Depth	0.013 - 0.02	mm

