

Xenoy* Resin IQ4840

Americas: COMMERCIAL

Xenoy iQ4840 (PBT+PC) resin is an environmental responsible, sustainable, and low carbon footprint resin. It is a 10% mineral filled resin with high modulus and ductile (HMD) characteristics. Xenoy iQ4840 offers a good balance of impact and ductility, excellent pull strength, good fatigue, provides Class A surface which is paintable, and excellent processibility. It is currently used in painted automotive doorhandles.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	59	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.9	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	130	%	ASTM D 638
Tensile Modulus, 5 mm/min	4000	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	104	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3500	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	58	MPa	ISO 527
Tensile Stress, break, 5 mm/min	54	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.8	%	ISO 527
Tensile Strain, break, 5 mm/min	120	%	ISO 527
Tensile Modulus, 1 mm/min	3800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	3450	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	250	J/m	ASTM D 256
Izod Impact, notched, -30°C	90	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	65	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	23	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	127	°C	ASTM D 1525



Xenoy* Resin IQ4840

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	98	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.6E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.6E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	128	°C	ISO 306
Vicat Softening Temp, Rate B/120	128	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	94	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.3	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.7 - 0.9	%	SABIC Method
Melt Flow Rate, 250°C/5.0 kgf	7	g/10 min	ASTM D 1238
Density	1.3	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.28	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	13	cm ³ /10 min	ISO 1133



Xenoy* Resin IQ4840

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	110	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	255 - 275	°C
Nozzle Temperature	250 - 265	°C
Front - Zone 3 Temperature	250 - 270	°C
Middle - Zone 2 Temperature	245 - 265	°C
Rear - Zone 1 Temperature	240 - 260	°C
Mold Temperature	40 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 80	rpm
Shot to Cylinder Size	50 - 80	%
Vent Depth	0.013 - 0.02	mm

