



LNP™ STAT-KON™ Compound DE0069F

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound DC-1006 FR SM

Product reorder name: DE0069F

LNP STAT-KON DE0069F is a compound based on Polycarbonate resin containing 30% Carbon Fiber. Added features of this material include: Electrically Conductive, Flame Retardant, Superior Molding.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	1480	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	1480	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.6	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	176600	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	2140	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2160	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	149200	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	1	MPa	ISO 527
Tensile Stress, break, 5 mm/min	137	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.2	%	ISO 527
Tensile Strain, break, 5 mm/min	1.2	%	ISO 527
Tensile Modulus, 1 mm/min	16670	MPa	ISO 527
Flexural Modulus, 2 mm/min	14560	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	47	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Multiaxial Impact	22	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	101	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	24	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	146	°C	ASTM D 648





LNP™ STAT-KON™ Compound DE0069F

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	142	°C	ASTM D 648
CTE, -30°C to 30°C, flow	7.E-06	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.E-06	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	148	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	143	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.36	-	ASTM D 792
Density	1.36	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.07	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.01 - 0.03	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.1 - 0.4	%	ASTM D 955
Density	1.36	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.13	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+00 - 4.E+00	Ohm	ASTM D 257





LNP™ STAT-KON™ Compound DE0069F

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

