



## LNP™ THERMOCOMP™ Compound MB006SXP

### Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound MB-1006 HS-S

Product reorder name: MB006SXP

LNP THERMOCOMP MB006SXP is a compound based on Polypropylene resin containing Glass Bead. Added features include: Heat Stabilized.

| TYPICAL PROPERTIES <sup>1</sup>       | TYPICAL VALUE | Unit              | Standard     |
|---------------------------------------|---------------|-------------------|--------------|
| <b>MECHANICAL</b>                     |               |                   |              |
| Tensile Stress, yield, 50 mm/min      | 25            | MPa               | ISO 527      |
| Tensile Strain, yield, 50 mm/min      | 7.1           | %                 | ISO 527      |
| Tensile Modulus, 1 mm/min             | 1900          | MPa               | ISO 527      |
| Flexural Stress, yield, 2 mm/min      | 36            | MPa               | ISO 178      |
| Flexural Modulus, 2 mm/min            | 1700          | MPa               | ISO 178      |
| <b>IMPACT</b>                         |               |                   |              |
| Izod Impact, unnotched 80*10*4 +23°C  | 20            | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C    | 4             | kJ/m <sup>2</sup> | ISO 180/1A   |
| <b>THERMAL</b>                        |               |                   |              |
| CTE, 23°C to 60°C, flow               | 1.07E-04      | 1/°C              | ISO 11359-2  |
| CTE, 23°C to 60°C, xflow              | 1.2E-04       | 1/°C              | ISO 11359-2  |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 62            | °C                | ISO 75/Af    |
| <b>PHYSICAL</b>                       |               |                   |              |
| Mold Shrinkage, flow (5)              | 1.2 - 1.6     | %                 | SABIC Method |
| Density                               | 1.12          | g/cm <sup>3</sup> | ISO 1183     |





## LNP™ THERMOCOMP™ Compound MB006SXP

Europe-Africa-Middle East: COMMERCIAL

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 80            | °C   |
| Drying Time                 | 4             | hrs  |
| Melt Temperature            | 225 - 250     | °C   |
| Front - Zone 3 Temperature  | 240 - 250     | °C   |
| Middle - Zone 2 Temperature | 215 - 225     | °C   |
| Rear - Zone 1 Temperature   | 195 - 205     | °C   |
| Mold Temperature            | 30 - 50       | °C   |
| Back Pressure               | 0.2 - 0.3     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |

