



LNP™ THERMOCOMP™ Compound MX92284
Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound PDX-M-92284
Product reorder name: MX92284

LNP THERMOCOMP MX92284 is a compound based on Polypropylene resin containing Proprietary Filler(s).

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	500	kgf/cm ²	ASTM D 638
Tensile Strain, break	3.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	48600	kgf/cm ²	ASTM D 638
Flexural Stress	7940	kgf/cm ²	ASTM D 790
Flexural Modulus	38500	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	43	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
PHYSICAL			
Density	1.03	g/cm ³	ASTM D 792





LNP™ THERMOCOMP™ Compound MX92284

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

