

Optema™ TC 114 Blown

Ethylene Methyl Acrylate Copolymer Resin

Product Description

OPTEMA TC 114 is an ethylene methyl acrylate copolymer specifically formulated to offer extrusion and property performance for blown film applications. It produces a soft, elastic film with good handling characteristics without additional additives. OPTEMA TC 114 can produce film under 1.0 mil thickness.

General

Additive	▪ Antiblock: 14000 ppm	▪ Slip: 3000 ppm	▪ Thermal Stabilizer: Yes
Applications	▪ Disposable Gloves	▪ Hospital Drapes	▪ Upholstery Film

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.948 g/cm ³	0.948 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	3.2 g/10 min	3.2 g/10 min	ASTM D1238
Methyl Acrylate Content	18.0 wt%	18.0 wt%	ExxonMobil Method
Peak Melting Temperature	185 °F	85 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	135 °F	57 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	2900 psi	20 MPa	ASTM D882
Tensile Strength at Break TD	2900 psi	20 MPa	ASTM D882
Elongation at Break MD	380 %	380 %	ASTM D882
Elongation at Break TD	670 %	670 %	ASTM D882
Secant Modulus MD - 1% Secant	7200 psi	49 MPa	ASTM D882
Secant Modulus TD - 1% Secant	7500 psi	51 MPa	ASTM D882
Dart Drop Impact	370 g	370 g	ASTM D1709A
Elmendorf Tear Strength MD	50 g	50 g	ASTM D1922
Elmendorf Tear Strength TD	310 g	310 g	ASTM D1922

