

Escorene™ Ultra UL 7741

Ethylene Vinyl Acetate Copolymer Resin

Product Description

Escorene Ultra UL 7741 is a very high flow, 26.7% VA copolymer that has very good compatibility with hydrocarbon and natural tackifiers and most waxes. It is suitable for making hot melt adhesives, sealants and wax blends.

General

Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Adhesives and Sealants ▪ Hot Melt Adhesives	▪ Industrial Sealants ▪ Wax Blends	
Form(s)	▪ Pellets		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.946 g/cm ³	0.946 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	43 g/10 min	43 g/10 min	ASTM D1238
Vinyl Acetate Content	26.7 wt%	26.7 wt%	ExxonMobil Method
Peak Melting Temperature	158 °F	70 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	133 °F	56 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break	> 580 psi	> 4.0 MPa	ASTM D638
Elongation at Break	> 800 %	> 800 %	ASTM D638
Flexural Modulus - 1% Secant	3100 psi	21 MPa	ASTM D790
Durometer Hardness			ASTM D2240
Shore A, 15 sec	78	78	
Shore D, 15 sec	22	22	

