

Escorene™ Ultra UL 00018

Ethylene Vinyl Acetate Copolymer Resin

Product Description

UL 00018 is a fractional MI copolymer of ethylene and vinyl acetate.

General

Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Agricultural Film ▪ Compounding	▪ Profile Extrusion ▪ Thick Film	▪ Wire and Cable Compounds

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.940 g/cm ³	0.940 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	0.37 g/10 min	0.37 g/10 min	ASTM D1238
Vinyl Acetate Content	17.5 wt%	17.5 wt%	ExxonMobil Method
Peak Melting Temperature	194 °F	90 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	154 °F	68 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	5200 psi	36 MPa	ASTM D882
Tensile Strength at Break TD	5200 psi	36 MPa	ASTM D882
Elongation at Break MD	610 %	610 %	ASTM D882
Elongation at Break TD	660 %	660 %	ASTM D882
Secant Modulus MD - 1% Secant	6500 psi	45 MPa	ASTM D882
Secant Modulus TD - 1% Secant	7300 psi	50 MPa	ASTM D882

