

Paxon™ AB50-003

High Density Polyethylene Resin

Product Description

AB50-003 is a blow molding grade high density polyethylene copolymer. This resin has very good stress crack resistance combined with high impact strength and rigidity.

General

Additive	<ul style="list-style-type: none"> Thermal Stabilizer: Yes Antistatic: No
Applications	<ul style="list-style-type: none"> Food Packaging Household and Industrial chemical containers Pharmaceutical Packaging Thermoformed Parts

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.950 g/cm ³	0.950 g/cm ³	ASTM D4883
Melt Index (190°C/2.16 kg)	0.30 g/10 min	0.30 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Brittleness Temperature	< -105 °F	< -76 °C	ASTM D746
Vicat Softening Temperature	255 °F	124 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	3900 psi	27 MPa	ASTM D638
Flexural Modulus	170000 psi	1200 MPa	ASTM D790
Environmental Stress-Crack Resistance 100% Igepal	70 hr	70 hr	ASTM D1693

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Impact Strength	90 ft·lb/in ²	190 kJ/m ²	ASTM D1822

