

ExxonMobil™ LDPE LD 102.LC

Low Density Polyethylene Resin

Product Description

LD 102.LC is a formulated homopolymer, garment film resin with good toughness. It is capable of being drawn-down to thin gauges.

General

Additive	- Antiblock: 3000 ppm - Slip: 1200 ppm	- Processing Aid: No - Thermal Stabilizer: No
Applications	- Blown Film - Cast Film	- Compounding - Garment Film - Laundry Film

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.921 g/cm ³	0.921 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	6.8 g/10 min	6.8 g/10 min	ASTM D1238
Peak Melting Temperature	232 °F	111 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	189 °F	87 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1400 psi	9.7 MPa	ASTM D882
Tensile Strength at Yield TD	1500 psi	10 MPa	ASTM D882
Tensile Strength at Break MD	2600 psi	18 MPa	ASTM D882
Tensile Strength at Break TD	2100 psi	15 MPa	ASTM D882
Elongation at Break MD	230 %	230 %	ASTM D882
Elongation at Break TD	530 %	530 %	ASTM D882
Secant Modulus MD - 1% Secant	25000 psi	170 MPa	ASTM D882
Secant Modulus TD - 1% Secant	30000 psi	200 MPa	ASTM D882
Dart Drop Impact	60 g	60 g	ASTM D1709A
Elmendorf Tear Strength MD	500 g	500 g	ASTM D1922
Elmendorf Tear Strength TD	210 g	210 g	ASTM D1922
Puncture Force	5 lbf	20 N	ExxonMobil Method
Puncture Energy	1.8 in-lb	0.20 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss	71	71	ASTM D2457
Haze	7.4 %	7.4 %	ASTM D1003

