

ExxonMobil™ LDPE LD 313.NF

Low Density Polyethylene Resin

Product Description

ExxonMobil™ LD 313.NF is a 3 wt% vinyl acetate copolymer. The vinyl acetate content of this resin provides good heat sealing and good cold temperature toughness when compared to LDPE homopolymers.

General

Additive	▪ Antiblock: 2500 ppm	▪ Slip: 800 ppm	▪ Thermal Stabilizer: Yes
Applications	▪ Carpet Backing ▪ Co-Extrusion Films ▪ Foams	▪ Form Fill And Seal Packaging ▪ Freezer Film ▪ High Clarity Film	▪ Lamination Film
Form(s)	▪ Pellets		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.925 g/cm ³	0.925 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	2.5 g/10 min	2.5 g/10 min	ASTM D1238
Vinyl Acetate Content	3.0 wt%	3.0 wt%	ExxonMobil Method
Peak Melting Temperature	223 °F	106 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	191 °F	88 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1300 psi	8.9 MPa	ASTM D882
Tensile Strength at Yield TD	1300 psi	9.2 MPa	ASTM D882
Tensile Strength at Break MD	3400 psi	23 MPa	ASTM D882
Tensile Strength at Break TD	2800 psi	19 MPa	ASTM D882
Elongation at Break MD	190 %	190 %	ASTM D882
Elongation at Break TD	520 %	520 %	ASTM D882
Secant Modulus MD - 1% Secant	21000 psi	150 MPa	ASTM D882
Secant Modulus TD - 1% Secant	25000 psi	170 MPa	ASTM D882
Dart Drop Impact	120 g	120 g	ASTM D1709A
Elmendorf Tear Strength MD	240 g	240 g	ASTM D1922
Elmendorf Tear Strength TD	150 g	150 g	ASTM D1922
Puncture Force	6 lbf	28 N	ExxonMobil Method
Puncture Energy	3.7 in·lb	0.42 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	77	77	ASTM D2457
Haze	5.1 %	5.1 %	ASTM D1003

