

ExxonMobil™ LLDPE LL 1107 Series

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ LL 1107 resins are fractional melt index ethylene 1-butene linear low density polyethylene blown film resins. Films made from LL 1107 resins have good stiffness and tensile strength. These resins' strength and drawability make them excellent for many film applications.

General

Additive	- LL 1107X93: Antiblock: 3500 ppm; Slip: 1000 ppm; Processing Aid: Yes; Thermal Stabilizer: Yes - LL 1107X95: Antiblock: 3500 ppm; Slip: 1700 ppm; Processing Aid: Yes; Thermal Stabilizer: Yes		
Applications	Blown Film	Garment Film	Produce Bags
Form(s)	Pellets		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.922 g/cm ³	0.922 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.80 g/10 min	0.80 g/10 min	ASTM D1238
Peak Melting Temperature	253 °F	123 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	219 °F	104 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1500 psi	10 MPa	ASTM D882
Tensile Strength at Yield TD	1600 psi	11 MPa	ASTM D882
Tensile Strength at Break MD	8000 psi	50 MPa	ASTM D882
Tensile Strength at Break TD	5000 psi	34 MPa	ASTM D882
Elongation at Break MD	540 %	540 %	ASTM D882
Elongation at Break TD	820 %	820 %	ASTM D882
Secant Modulus MD - 1% Secant	34000 psi	230 MPa	ASTM D882
Secant Modulus TD - 1% Secant	39000 psi	270 MPa	ASTM D882
Dart Drop Impact	70 g	70 g	ASTM D1709A
Elmendorf Tear Strength MD	50 g	50 g	ASTM D1922
Elmendorf Tear Strength TD	620 g	620 g	ASTM D1922
Puncture Force	8 lbf	34 N	ExxonMobil Method
Puncture Energy	15 in-lb	1.7 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	34	34	ASTM D2457
Haze	17 %	17 %	ASTM D1003

