

ExxonMobil™ LLDPE LL 8446.21

Linear Low Density Polyethylene Resin

Product Description

LL 8446 is a linear low density butene copolymer designed to offer excellent processability, whiteness, and fast grinding rate. This UV stabilized resin is ideally suited for applications that require excellent dimensional control and low warpage.

General

Additive	▪ Long Term UV-8 Stabilizer: Yes		
Applications	▪ Consumer Articles	▪ Tanks	
	▪ General Purpose Articles	▪ Toys	

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.936 g/cm ³	0.936 g/cm ³	ISO 1183
Melt Index (190°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ISO 1133

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	126 °F	52 °C	ASTM D648
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	97 °F	36 °C	ASTM D648
Peak Melting Temperature	257 °F	125 °C	ASTM D3418

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	2500 psi	17 MPa	ASTM D638
Tensile Stress at Yield	2500 psi	17 MPa	ISO 527-2/1A/50
Tensile Strain at Yield	10 %	10 %	ISO 527-2/50
Flexural Modulus - 1% Secant	110000 psi	730 MPa	ASTM D790B
Flexural Modulus	100000 psi	700 MPa	ISO 178
Environmental Stress-Crack Resistance			
0.0787 in (2.00 mm), 10% Igepal, F50	30 hr	30 hr	ASTM D1693
10% Igepal, F50	20 hr	20 hr	ASTM D1693A
100% Igepal, F50	40 hr	40 hr	ASTM D1693A

