

ExxonMobil™ NTX Series

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ NTX Super Strength Series are ethylene 1-hexene linear low density polyethylene resins designed for applications requiring exceptional strength, especially tear, for maximum downgauging potential. ExxonMobil™ NTX resins are formulated with slip and antiblock, both with and without processing aid, for use in all high performance film applications.

General

Additive	- NTX 095: Antiblock: 8000 ppm; Slip: 1400 ppm; Processing Aid: No; Thermal Stabilizer: Yes - NTX 141: Antiblock: 6500 ppm; Slip: 1400 ppm; Processing Aid: Yes; Thermal Stabilizer: Yes		
Applications	- General Packaging - Ice Bags	- Trash Bags - Trash Can Liners	
Form(s)	Pellets		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.917 g/cm ³	0.917 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.90 g/10 min	0.90 g/10 min	ASTM D1238
Peak Melting Temperature	255 °F	124 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1200 psi	8.6 MPa	ASTM D882
Tensile Strength at Yield TD	1200 psi	8.6 MPa	ASTM D882
Tensile Strength at Break MD	8100 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	6800 psi	47 MPa	ASTM D882
Elongation at Break MD	550 %	550 %	ASTM D882
Elongation at Break TD	710 %	710 %	ASTM D882
Secant Modulus MD - 1% Secant	23000 psi	160 MPa	ASTM D882
Secant Modulus TD - 1% Secant	24000 psi	170 MPa	ASTM D882
Dart Drop Impact	580 g	580 g	ASTM D1709A
Elmendorf Tear Strength MD	390 g	390 g	ASTM D1922
Elmendorf Tear Strength TD	410 g	410 g	ASTM D1922
Puncture Force	8 lbf	36 N	ExxonMobil Method
Puncture Energy	22 in·lb	2.5 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	33	33	ASTM D2457
Haze	25 %	25 %	ASTM D1003

