

ExxonMobil™ LLDPE LL 1001AV

Linear Low Density Polyethylene Resin

产品说明

ExxonMobil™ LL 1001AV is an ethylene 1-butene linear low density polyethylene resin that offers excellent drawdown and puncture resistance combined with high gloss and clarity. It is frequently used as a blend partner with LDPE resins to improve film properties and processability. TnPP is not intentionally added to LL 1001AV resin.

总览

添加剂	- 开口: 否 - 爽滑: 否	- 加工助剂: 否 - 热稳定剂: 是	
应用	- 包装膜 - 冰袋 - 成形、填充和封口包装 - 成衣包装膜 - 吹膜 - 多层包装膜 - 复合膜 - 工业包装	- 工业用内衬 - 购物袋 - 垃圾袋 - 垃圾袋 - 冷冻膜 - 面包袋 - 内衬袋 - 农产品包装袋	- 农用薄膜 - 食品包装 - 通用包装 - 箱中袋 - 重型包装袋 - 自立袋 - 阻隔性食品包装
形式	粒子		

物理性能	典型数值 (英制)	典型数值 (公制)	测试方法
密度	0.918 g/cm ³	0.918 g/cm ³	ASTM D1505
熔融指数 (190° C/2.16 kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238
熔融峰值温度	248 ° F	120 ° C	ExxonMobil Method

热性能	典型数值 (英制)	典型数值 (公制)	测试方法
维卡软化温度	207 ° F	97 ° C	ASTM D1525

薄膜	典型数值 (英制)	典型数值 (公制)	测试方法
MD 屈服拉伸强度	1400 psi	9.3 MPa	ASTM D882
TD 屈服拉伸强度	1500 psi	10 MPa	ASTM D882
MD 断裂拉伸强度	6500 psi	45 MPa	ASTM D882
TD 断裂拉伸强度	5200 psi	36 MPa	ASTM D882
MD 断裂伸长率	550 %	550 %	ASTM D882
TD 断裂伸长率	910 %	910 %	ASTM D882
割线模量 MD - 1% 正割	26000 psi	180 MPa	ASTM D882
割线模量 TD - 1% 正割	31000 psi	210 MPa	ASTM D882
落锤冲击	90 g	90 g	ASTM D1709A
埃尔曼多夫抗撕强度 MD	110 g	110 g	ASTM D1922
埃尔曼多夫抗撕强度 TD	450 g	450 g	ASTM D1922
穿刺力	9 lbf	40 N	ExxonMobil Method
穿刺能	26 in · lb	3.0 J	ExxonMobil Method

光学性能	典型数值 (英制)	典型数值 (公制)	测试方法
光泽度 (45°)	51	51	ASTM D2457
雾度	18 %	18 %	ASTM D1003

