

ExxonMobil™ LLDPE LL 3404.48

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ LL 3404.48 resin is an ethylene 1-hexene medium density cast film grade for applications requiring high strength and high stiffness. Films produced from this resin exhibit good tensile and puncture resistance properties.

General

Additive	- Antiblock: No - Slip: No	- Processing Aid: No - Thermal Stabilizer: Yes
Applications	- Agricultural Film - Cast Film	- Diaper Backsheet - Overwrap Film
Form(s)	Pellets	

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.942 g/cm ³	0.942 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	4.3 g/10 min	4.3 g/10 min	ASTM D1238
Peak Melting Temperature	261 °F	127 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	246 °F	119 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	2400 psi	17 MPa	ASTM D882
Tensile Strength at Yield TD	2500 psi	17 MPa	ASTM D882
Tensile Strength at Break MD	5600 psi	39 MPa	ASTM D882
Tensile Strength at Break TD	4300 psi	30 MPa	ASTM D882
Elongation at Break MD	600 %	600 %	ASTM D882
Elongation at Break TD	810 %	810 %	ASTM D882
Secant Modulus MD - 1% Secant	62000 psi	430 MPa	ASTM D882
Secant Modulus TD - 1% Secant	73000 psi	500 MPa	ASTM D882
Dart Drop Impact	< 50 g	< 50 g	ASTM D1709A
Elmendorf Tear Strength MD	20 g	20 g	ASTM D1922
Elmendorf Tear Strength TD	110 g	110 g	ASTM D1922
Puncture Force	4 lbf	16 N	ExxonMobil Method
Puncture Energy	2.4 in-lb	0.27 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	83	83	ASTM D2457
Haze	3.8 %	3.8 %	ASTM D1003

