

Exceed™ XP 8318ML

高性能聚合物

产品说明

Exceed™ XP 8318ML is an eXtreme Performance ethylene 1-hexene copolymer that offers step-out toughness, high flex-crack resistance and increased output with excellent bubble stability for a range of blown film applications. TnPP is not intentionally added to Exceed™ XP 8318ML. Exceed™ XP 8318ML - when eXtreme Performance matters.

总览

添加剂	▪ EXCEED XP 8318ML: 开口: 否; 爽滑: 否; 加工助剂: 是; 热稳定剂: 是		
应用	▪ Blown Silage	▪ 农用薄膜	▪ 液体包装
	▪ Construction Liners	▪ 软包装	

物理性能	典型数值 (英制)	典型数值 (公制)	测试方法
密度	0.918 g/cm ³	0.918 g/cm ³	ASTM D1505
熔融指数 (190° C/2.16 kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238
熔融峰值温度	250 ° F	121 ° C	ExxonMobil Method

薄膜	典型数值 (英制)	典型数值 (公制)	测试方法
MD 屈服拉伸强度	1400 psi	9.7 MPa	ASTM D882
TD 屈服拉伸强度	1500 psi	10 MPa	ASTM D882
MD 断裂拉伸强度	9300 psi	60 MPa	ASTM D882
TD 断裂拉伸强度	7500 psi	50 MPa	ASTM D882
MD 断裂伸长率	370 %	370 %	ASTM D882
TD 断裂伸长率	660 %	660 %	ASTM D882
割线模量 MD - 1% 正割	28000 psi	190 MPa	ASTM D882
割线模量 TD - 1% 正割	33000 psi	230 MPa	ASTM D882
落锤冲击	670 g	670 g	ASTM D1709
埃尔曼多夫抗撕强度 MD	370 g	370 g	ASTM D1922
埃尔曼多夫抗撕强度 TD	470 g	470 g	ASTM D1922
穿刺力	10 lbf	44 N	ExxonMobil Method
穿刺能	29 in · lb	3.2 J	ExxonMobil Method

光学性能	典型数值 (英制)	典型数值 (公制)	测试方法
光泽度 (45°)	20	20	ASTM D2457
雾度	> 30 %	> 30 %	ASTM D1003

