

Exceed™ XP 6026 Series

高性能聚合物

产品说明

Exceed™ XP 6026 is an eXtreme Performance linear low density polyethylene 1-hexene copolymer that is especially designed to have high melt strength and superior tensile, impact, and puncture properties. The combination of high toughness, melt stability and good sealing performance makes this grade a versatile blown film resin. TnPP is not intentionally added to Exceed™ XP 6026. Exceed™ XP 6026 - when eXtreme Performance matters.

总览

添加剂	- Exceed XP 6026MQ: 开口: 否; 爽滑: 否; 加工助剂: 否; 热稳定剂: 是 - Exceed XP 6026ML: 开口: 否; 爽滑: 否; 加工助剂: 是; 热稳定剂: 是
应用	- Construction Liners - Geomembrane - Greenhouse Film - 复合膜 - 食品包装 - 收缩膜 - 重型包装袋

物理性能	典型数值 (英制)	典型数值 (公制)	测试方法
密度	0.916 g/cm ³	0.916 g/cm ³	ASTM D1505
熔融指数 (190° C/2.16 kg)	0.20 g/10 min	0.20 g/10 min	ASTM D1238
熔融峰值温度	230 ° F	110 ° C	ExxonMobil Method

薄膜	典型数值 (英制)	典型数值 (公制)	测试方法
MD 屈服拉伸强度	1300 psi	8.9 MPa	ASTM D882
TD 屈服拉伸强度	1400 psi	9.9 MPa	ASTM D882
MD 断裂拉伸强度	9400 psi	70 MPa	ASTM D882
TD 断裂拉伸强度	9700 psi	70 MPa	ASTM D882
MD 断裂伸长率	390 %	390 %	ASTM D882
TD 断裂伸长率	640 %	640 %	ASTM D882
割线模量 MD - 1% 正割	26000 psi	180 MPa	ASTM D882
割线模量 TD - 1% 正割	32000 psi	220 MPa	ASTM D882
落锤冲击 ²	680 g	680 g	ASTM D1709
埃尔曼多夫抗撕强度 MD	60 g	60 g	ASTM D1922
埃尔曼多夫抗撕强度 TD	400 g	400 g	ASTM D1922
穿刺力	15 lbf	67 N	ExxonMobil Method
穿刺能	43 in · lb	4.8 J	ExxonMobil Method

光学性能	典型数值 (英制)	典型数值 (公制)	测试方法
光泽度 (45°)	44	44	ASTM D2457
雾度	12 %	12 %	ASTM D1003

