

ExxonMobil™ PP1304E4

Polypropylene Homopolymer

Product Description

A homopolymer resin designed for injection molding applications requiring excellent flow and good mechanical properties. It is suitable for general purpose applications such as toys, household goods, caps and closures.

General

Uses	▪ Caps ▪ Closures	▪ Household Goods ▪ Toys
Appearance	▪ Natural Color	
Form(s)	▪ Pellets	
Processing Method	▪ Compounding ▪ Injection Molding	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13 g/10 min	13 g/10 min	ASTM D1238
Density	0.9 g/cm ³	0.9 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield			ASTM D638
2.0 in/min (51 mm/min)	5110 psi	35.2 MPa	
Tensile Stress at Yield	4840 psi	33.4 MPa	ISO 527-2/50
Elongation at Yield (2.0 in/min (51 mm/min))	9.4 %	9.4 %	ASTM D638
Tensile Strain at Yield	7.1 %	7.1 %	ISO 527-2/50
Tensile Modulus - Chord	230000 psi	1580 MPa	ISO 527-2/1
Flexural Modulus - 1% Secant			
0.051 in/min (1.3 mm/min)	218000 psi	1500 MPa	ASTM D790A
0.51 in/min (13 mm/min)	256000 psi	1770 MPa	ASTM D790B
Flexural Modulus (0.079 in/min (2.0 mm/min))	207000 psi	1430 MPa	ISO 178

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (73°F (23°C))	0.41 ft-lb/in	22 J/m	ASTM D256A
Notched Izod Impact Strength (73°F (23°C))	1.5 ft-lb/in ²	3.1 kJ/m ²	ISO 180/1A
Charpy Notched Impact Strength (73°F (23°C))	1.0 ft-lb/in ²	2.2 kJ/m ²	ISO 179/1eA
Gardner Impact			ASTM D5420
73°F (23°C), 0.125 in (3.18 mm), Geometry GC	86.1 in-lb	9.73 J	

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (1.80 MPa)	126 °F	52.0 °C	ISO 75-2/Af
Heat Deflection Temperature (0.45 MPa)	177 °F	80.6 °C	ISO 75-2/Bf
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	198 °F	92.4 °C	ASTM D648
DTUL @ 66psi - Annealed	237 °F	114 °C	ASTM D648

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Rockwell Hardness	107	107	ASTM D785
Shore Hardness (15 sec)	67	67	ISO 868

