

## ExxonMobil™ PP3155E3

## Polypropylene Homopolymer

## **Product Description**

A homopolymer resin designed for spunbond nonwovens. The resin is particularly suited for excellent spinning for uniform, high quality fabrics. Formulated for applications requiring low color and low gas fading discoloration.

General				
Features	<ul> <li>Gas-fading Resistant</li> </ul>	<ul> <li>Good Processability</li> </ul>		
Uses	<ul><li>Fibers</li><li>Industrial Applications</li></ul>	<ul><li>Medical/Healthcare Applications</li><li>Personal Care</li></ul>	Spunbond Nonwovens	
Appearance	<ul> <li>Natural Color</li> </ul>			
Form(s)	<ul> <li>Pellets</li> </ul>			
Processing Method	<ul> <li>Filament Extrusion</li> </ul>	<ul> <li>Spunbond Nonwovens</li> </ul>		
Physical	Typical Value (Englis	sh) Typical Value	(SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	36 g/10 r	min 36	g/10 min	ASTM D1238
Density	0.9 g/cm <sup>3</sup>	0.9	g/cm³	ExxonMobil Method



