

Santoprene™ 211-45

Thermoplastic Vulcanizate

Product Description

A soft, colorable, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of injection molding applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Recommended for applications requiring excellent flex fatigue resistance.
- Excellent ozone resistance.
- UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component.
- Used in sealing applications.

General

Applications	▪ Automotive - Grips ▪ Automotive - Interior Mat	▪ Industrial - Seals and Gaskets ▪ Soft Touch Grips	▪ Tubing
Uses	▪ Automotive Applications	▪ Gaskets	▪ Seals
Agency Ratings	▪ UL QMFZ2	▪ UL QMFZ8	
RoHS Compliance	▪ RoHS Compliant		
Automotive Specifications	▪ CHRYSLER MS-AR-100 BMN	▪ FORD WSD-M2D378-A4	
UL File Number	▪ E80017		
Color	▪ Natural Color		
Form(s)	▪ Pellets		
Processing Method	▪ Injection Molding	▪ Multi Injection Molding	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.960	0.960	ASTM D792
Density	0.960 g/cm ³	0.960 g/cm ³	ISO 1183

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore A, 15 sec, 73°F (23°C)	49	49	

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	203 psi	1.40 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	203 psi	1.40 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	508 psi	3.50 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	508 psi	3.50 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	340 %	340 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	340 %	340 %	ISO 37
Compression Set			ASTM D395B
73°F (23°C), 22 hr, Type 1	11 %	11 %	
257°F (125°C), 70 hr, Type 1	35 %	35 %	
Compression Set			ISO 815
73°F (23°C), 22 hr, Type A	11 %	11 %	
257°F (125°C), 70 hr, Type A	35 %	35 %	



Santoprene™ 211-45
Thermoplastic Vulcanizate

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Brittleness Temperature	-80 °F	-62 °C	ASTM D746
Brittleness Temperature	-80 °F	-62 °C	ISO 812
RTI Elec	212 °F	100 °C	UL 746
RTI Str			UL 746
0.04 in (1.0 mm)	194 °F	90.0 °C	
0.12 in (3.0 mm)	203 °F	95.0 °C	

Electrical	Typical Value (English)	Typical Value (SI)	Test Based On
Dielectric Strength			ASTM D149
73°F (23°C), 0.0787 in (2.00 mm)	770 V/mil	30 kV/mm	
Dielectric Constant			ASTM D150
73°F (23°C), 0.0799 in (2.03 mm)	2.40	2.40	
Dielectric Constant			IEC 60250
73°F (23°C), 0.0799 in (2.03 mm)	2.40	2.40	

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82 °C
Drying Time	3.0 hr	3.0 hr
Suggested Max Moisture	0.080 %	0.080 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	350 to 380 °F	177 to 193 °C
Middle Temperature	355 to 390 °F	179 to 199 °C
Front Temperature	355 to 400 °F	179 to 204 °C
Nozzle Temperature	375 to 445 °F	191 to 229 °C
Processing (Melt) Temp	380 to 465 °F	193 to 241 °C
Mold Temperature	50 to 125 °F	10 to 52 °C
Injection Rate	Fast	Fast
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	100 to 200 rpm	100 to 200 rpm
Clamp Tonnage	3.0 to 5.0 tons/in ²	41 to 69 MPa
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm
Screw L/D Ratio	16.0:1.0 to 20.0:1.0	16.0:1.0 to 20.0:1.0
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	2.0:1.0 to 2.5:1.0
Vent Depth	1.0E-3 in	0.025 mm

Injection Notes

Santoprene TPV is incompatible with acetal and PVC. An SPI/SPE #3 finish is recommended (do not polish). For more information regarding processing and mold design, please consult our Injection Molding Guide.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-23 %	-23 %	ASTM D573
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-23 %	-23 %	ISO 188
Change in Ultimate Elongation in Air 302°F (150°C), 168 hr	26 %	26 %	ASTM D573
Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr	26 %	26 %	ISO 188
Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr	1.0	1.0	ASTM D573
Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr	1.0	1.0	ISO 188



Santoprene™ 211-45
Thermoplastic Vulcanizate

Flammability	Typical Value (English)	Typical Value (SI)	Test Based On
Flame Rating			UL 94
0.04 in (1.0 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

