

Diamond Asa S150

Acrylonitrile Styrene Acrylate

LyondellBasell Industries

Engineering Plastics

General			
Features	• Good Weather Resistance	• High Impact Resistance	
Agency Ratings	• EC 1907/2006 (REACH)	• EU 2002/96/EC (WEEE)	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.06	1.06 g/cm ³	ASTM D792
73°F (23°C)	1.06 g/cm ³	1.06 g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR)			ASTM D1238 ISO 1133
220°C/10.0 Kg	15 g/10 min	15 g/10 min	
230°C/3.8 Kg	3.9 g/10 min	3.9 g/10 min	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength - Flow			
Yield, 73°F (23°C), Injection Molded ¹	6240 psi	43.0 MPa	ASTM D638
Yield, 73°F (23°C), Injection Molded	6350 psi	43.8 MPa	ISO 527-2
Flexural Modulus - Chord, Flow			
73°F (23°C), Injection Molded	316000 psi	2180 MPa	ASTM D790
73°F (23°C), Injection Molded	315000 psi	2170 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F (-30°C), Injection Molded	3.9 ft·lb/in ²	8.2 kJ/m ²	
73°F (23°C), Injection Molded	8.4 ft·lb/in ²	18 kJ/m ²	
Notched Izod Impact			
Flow : -22°F (-30°C), Injection Molded	2.0 ft·lb/in	110 J/m	ASTM D256
Flow : 73°F (23°C), Injection Molded	4.8 ft·lb/in	260 J/m	ASTM D256
-22°F (-30°C), Injection Molded	3.7 ft·lb/in ²	7.8 kJ/m ²	ISO 180
73°F (23°C), Injection Molded	9.8 ft·lb/in ²	21 kJ/m ²	ISO 180

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
R-scale, 73°F (23°C), Injection Molded	100	100	





Diamond Asa S150


Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed, Injection Molded	193 °F	89.2 °C	ASTM D648
66 Psi (0.45 Mpa), Unannealed	193 °F	89.3 °C	ISO 75-2/B
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm), Injection Molded	170 °F	76.7 °C	ASTM D648
264 Psi (1.8 Mpa), Unannealed, 0.250 In (6.35 Mm)	181 °F	82.8 °C	ASTM D648
264 Psi (1.8 Mpa), Unannealed	170 °F	76.6 °C	ISO 75-2/A
Vicat Softening Temperature			
--	216 °F	102 °C	ASTM D1525 ²
--	215 °F	102 °C	ISO 306
CLTE			
Flow : -22 To 176°f (-30 To 80°c)	5.2E-5 in/in/°F	9.3E-5 cm/cm/°C	ISO 11359-2
Transverse : -22 To 176°f (-30 To 80°c)	5.4E-5 in/in/°F	9.8E-5 cm/cm/°C	



Diamond Asa S150

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Suggested Shot Size	40 to 70 %	40 to 70 %
Rear Temperature	446 to 500 °F	230 to 260 °C
Middle Temperature	450 to 509 °F	232 to 265 °C
Front Temperature	455 to 522 °F	235 to 272 °C
Nozzle Temperature	428 to 522 °F	220 to 272 °C
Processing (Melt) Temp	428 to 522 °F	220 to 272 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Rate	Fast	Fast
Back Pressure	75.0 to 150 psi	0.517 to 1.03 MPa

Notes
¹ 2.0 in/min (50 mm/min)
² Loading 1 (10 N)

Notes
These are typical property values not to be construed as specification limits.

