

Diamond Asa S510

Acrylonitrile Styrene Acrylate

LyondellBasell Industries

Engineering Plastics

General			
Features	• Good Weather Resistance	• Medium Impact Resistance	
Agency Ratings	• EC 1907/2006 (REACH)	• EU 2002/96/EC (WEEE)	
RoHS Compliance	• RoHS Compliant		
UL File Number	• E150937		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/3.8 Kg)	6.5 g/10 min	6.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield)	6400 psi	44.1 MPa	ASTM D638
Flexural Modulus - Tangent ³	330000 psi	2280 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	2.5 ft·lb/in	130 J/m	


Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm)	181 °F	82.8 °C	
Vicat Softening Temperature	198 °F	92.2 °C	ASTM D1525 ⁴

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94



Diamond Asa S510

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Suggested Shot Size	40 to 70 %	40 to 70 %
Rear Temperature	446 to 500 °F	230 to 260 °C
Middle Temperature	450 to 509 °F	232 to 265 °C
Front Temperature	455 to 522 °F	235 to 272 °C
Nozzle Temperature	428 to 522 °F	220 to 272 °C
Processing (Melt) Temp	428 to 522 °F	220 to 272 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Rate	Fast	Fast
Back Pressure	75.0 to 150 psi	0.517 to 1.03 MPa

Notes

- ¹ Procedure A
- ² 2.0 in/min (51 mm/min)
- ³ 0.050 in/min (1.3 mm/min)
- ⁴ Loading 1 (10 N)

Notes

These are typical property values not to be construed as specification limits.

