

Schulablend (ASA/PA) M/MW UV K2358

Acrylonitrile Styrene Acrylate + PA

LyondellBasell Industries

Engineering Plastics

Product Description

ASA/PA injection molding grade with excellent light stability, impact properties and with high heat resistance

General

Processing Method • Injection Molding

Physical	Dry	Conditioned	Unit	Test Method
Density	1.09	--	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (260°C/5.0 Kg)	3.8	--	cm ³ /10min	ISO 1133
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	261000 (1800)	116000 (800)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Yield)	6380 (44.0)	4930 (34.0)	psi (MPa)	ISO 527-2/1A/50
Nominal Tensile Strain at Break	> 100	> 200	%	ISO 527-2/1A/50
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	4.8 (10)	--	ft·lb/in ² (kJ/m ²)	
-4°F (-20°C)	7.1 (15)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	48 (100)	59 (130)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	No Break	--		
-4°F (-20°C)	No Break	--		
73°F (23°C)	No Break	No Break		
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	13800 (95.0)	--	psi (MPa)	ISO 2039-1
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Af
264 Psi (1.8 Mpa), Unannealed	205 (96.0)	--	°F (°C)	
Vicat Softening Temperature				
--	257 (125)	--	°F (°C)	ISO 306/B50
--	406 (208)	--	°F (°C)	ISO 306/A50

Additional Information

The tradename "Schulablend" may be abbreviated "SBL" in documents or on labels.

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

