

Technical Data Sheet

Microthene MN71020

Low Density Polyethylene



Product Description

Microthene G polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. *Microthene* G powders combine the unique properties of a polyolefin resin with a small ground particle size.

Application	Automotive Parts; Colour Concentrates; Industrial; Interior Automotive Applications; Structural Parts
Market	Consumer Products; Flexible Packaging; Healthcare; Industrial, Building & Construction
Processing Method	Powders

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	22	g/10 min	22	g/10 min	ASTM D1238
Density, (23 °C)	0.915	g/cm ³	0.915	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus	33000	psi	228	MPa	ASTM D790
Tensile Strength at Break	1350	psi	9.3	MPa	ASTM D638
Tensile Elongation at Break	610	%	610	%	ASTM D638
Hardness					
Shore Hardness					
(Shore D, max)	49		49		ASTM D2240
(Shore D, 15 sec)	43		43		ASTM D2240
Thermal					
Vicat Softening Point	177.8	°F	81.0	°C	ASTM D1525
Low Temperature Brittleness	-30.3	°F	-34.6	°C	ASTM D746
Peak Melting Point	216.9	°F	102.7	°C	ASTM D3418
Additional Information					
Particle Shape	Irregular		Irregular		LYB Method
Average Particle Size	50	mesh	50	mesh	LYB Method

