

Icorene 2550

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

ICORENE® 2550 is a linear low density polyethylene powder specifically developed for rotational moulding.

This grade has been designed for applications requiring good processability, toughness and flexibility and is suitable in many different applications.

General

Additive	• UV Stabilizer		
Features	• Good Flexibility • Good Processability	• Good Toughness • UV Resistant	
Uses	• Flotation Devices	• Furniture	• Outdoor Furnishings
Appearance	• Natural Color	• Unspecified Color	
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.924 g/cm ³	0.924 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 Kg)	3.6 g/10 min	3.6 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield	2320 psi	16.0 MPa	
Break	1600 psi	11.0 MPa	
Tensile Elongation (Break)	> 1000 %	> 1000 %	ASTM D638
Flexural Modulus	63800 psi	440 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹ (-4°F (-20°C))	4.50 in·lb/mil	200 J/cm	Internal Method
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	52	52	ASTM D2240

Notes

¹ Based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

