

Icorene 1041

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

ICORENE® 1041 is a linear low density polyethylene specifically developed for rotational moulding.

This grade is suitable for use in general purpose applications. It has a good balance of properties such as toughness, easy flow and stiffness.

General

Additive	• UV Stabilizer		
Features	• Good Flow • Good Processability	• Good Stiffness • Good Toughness	• UV Resistant
Uses	• Agricultural Tanks	• Containers	• General Purpose
Appearance	• Natural Color	• Unspecified Color	
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.932 g/cm³	0.932 g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 Kg)	4.4 g/10 min	4.4 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield	2470 psi	17.0 MPa	
Break	2900 psi	20.0 MPa	
Tensile Elongation			ASTM D638
Yield	28 %	28 %	
Break	1300 %	1300 %	
Flexural Modulus	71100 psi	490 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹			Internal Method
-40°F (-40°C)	4.27 in·lb/mil	190 J/cm	
-4°F (-20°C)	4.05 in·lb/mil	180 J/cm	
73°F (23°C)	3.15 in·lb/mil	140 J/cm	

Notes

¹ Based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

