

GA 818-073

Linear Low Density Polyethylene Blow Molding Grade

Melt Index 0.75 Density 0.9205

Applications

PETROTHENE GA 818-073 offers the high environmental stress crack resistance characteristics of linear low density polyethylene with the processing properties needed for blowmolding and extrusion applications. The broad molecular weight distribution of GA 818-073 combines good melt strength with a significantly reduced tendency to melt fracture, two drawbacks common to conventional fractional melt index LLDPE resins. Applications for this resin include beverage and drip irrigation tubing, squeeze tubes and bottles for pharmaceutical and personal care product packaging, drum liners, highway traffic channellizers and other large, blow molded parts.

Processing Techniques

Processing conditions can only be recommended when the type of equipment and the end-use application are known. For further suggestions, please contact your Equistar sales representative.

Regulatory Status

GA 818-073 meets the specifications of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows for the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

Physical Properties

Property	Value*	Units	ASTM Test Method
Melt Index	0.75	g/10 min	D 1238
Density	0.9205	g/cc	D 1505
Tensile Strength @ Break	2,170	psi	D 638**
Elongation @ Break	>700	%	D 638**
Flexural Modulus	40,000	psi	D 790
Low Temperature Brittleness, F ₅₀	<-42	°C	D 746***
Heat Deflection Temperature @66 psi	48	°C	D 648
Vicat Softening Point	88	°C	D 1525
Hardness, Shore D	51		D 2240
Environmental Stress Crack Resistance, F ₅₀	>1,000	hrs	D 2561

* These are nominal values only and are not to be construed as specific product limits.

** Type IV specimen

*** Injection molded specimen

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

