

POLYLUX[®] (MABS) Typ C4

Methyl Methacrylate / ABS

Engineering Plastics

Product Description

Transparent MABS for extrusion and parts of high wall thickness

General

Processing Method	• Extrusion	• Injection Molding
Resin ID (ISO 1043)	• MABS	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.10 g/cm ³	1.10 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	2.00 cm ³ /10min	2.00 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	290000 psi	2000 MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	6960 psi	48.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	4.0 %	4.0 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	3.3 ft·lb/in ²	7.0 kJ/m ²	ISO 179/1eA
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	13900 psi	96.0 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	198 °F	92.0 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	172 °F	78.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	217 °F	103 °C	ISO 306/A50
--	201 °F	94.0 °C	ISO 306/B50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Notes

These are typical property values not to be construed as specification limits.

