

Polyaxis LP 8000

Metallocene High Density Polyethylene

LyondellBasell Industries

Rotomolding

Product Description

PolyAxis LP-8000 is a high density polyethylene intended for the rotational molding industry. This stiff yet tough compound has been used in watercraft with good success.

General

Additive	• Long Term UV-10 Stabilizer
Appearance	• Colors Available
Forms	• Pellets • Powder
Processing Method	• Rotational Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	0.947	0.945 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 Kg)	3.6 g/10 min	3.6 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 10% Igepal, Compression Molded, F50	6.00 hr	6.00 hr	ASTM D1693
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield, Rotational Molded)	3200 psi	22.1 MPa	ASTM D638
Tensile Elongation ² Break, Rotational Molded	500 %	500 %	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	145000 psi	1000 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 In (3.18 Mm), Rotational Molded	65 ft·lb	88 J	
-40°F (-40°C), 0.250 In (6.35 Mm), Rotational Molded ³	> 190 ft·lb	> 258 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed, 0.125 In (3.18 Mm), Rotational Molded	160 °F	71.1 °C	
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm), Rotational Molded	103 °F	39.3 °C	

Notes

¹ Compression Molded

² 2.0 in/min (51 mm/min)

³ Dart Weight 20 lbs

Notes

These are typical property values not to be construed as specification limits.

