

Schulamid 6 MV 14 FR

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Product Description

Medium viscosity flame-retardant Polyamide 6 grade; halogen- and phosphorus-free

General

Features	• Flame Retardant	• Halogen Free	• Medium Viscosity
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA 6 FR(30)		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.17	--	g/cm ³	ISO 1183/A

Viscosity Number	145	--	cm ³ /g	ISO 307
------------------	-----	----	--------------------	---------

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	493000 (3400)	160000 (1100)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Yield)	11600 (80.0)	5510 (38.0)	psi (MPa)	ISO 527-2/1A/50
Tensile Strain (Yield)	3.0	28	%	ISO 527-2/1A/50

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	2.9 (6.0)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	3.8 (8.0)	6.2 (13)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	No Break	No Break		
73°F (23°C)	No Break	No Break		

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	428 (220)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	176 (80.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	401 (205)	--	°F (°C)	ISO 306/B50
--	428 (220)	--	°F (°C)	ISO 306/A50
Ball Pressure Test (392°F (200°C))	Pass	--		IEC 60695-10-2



Schulamid 6 MV 14 FR

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
RTI Elec				UL 746B
0.030 In (0.75 Mm)	266 (130)	--	°F (°C)	
0.06 In (1.5 Mm)	266 (130)	--	°F (°C)	
0.12 In (3.0 Mm)	266 (130)	--	°F (°C)	
RTI Imp				UL 746B
0.030 In (0.75 Mm)	176 (80.0)	--	°F (°C)	
0.06 In (1.5 Mm)	185 (85.0)	--	°F (°C)	
0.12 In (3.0 Mm)	185 (85.0)	--	°F (°C)	
RTI Str				UL 746B
0.030 In (0.75 Mm)	221 (105)	--	°F (°C)	
0.06 In (1.5 Mm)	239 (115)	--	°F (°C)	
0.12 In (3.0 Mm)	311 (155)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Comparative Tracking Index	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.030 In (0.75 Mm)	PLC 0	--		
0.06 In (1.5 Mm)	PLC 0	--		
0.12 In (3.0 Mm)	PLC 0	--		
Hot-wire Ignition (HWI)				UL 746A
0.030 In (0.75 Mm)	PLC 3	--		
0.06 In (1.5 Mm)	PLC 3	--		
0.12 In (3.0 Mm)	PLC 2	--		
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.0295 In (0.750 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
0.0591 In (1.50 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
0.118 In (3.00 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	





Schulamid 6 MV 14 FR


Polyamide 6
LyondellBasell Industries
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94 IEC 60695-11-10, -20
0.030 In (0.75 Mm)	V-0	--		
0.06 In (1.5 Mm)	V-0	--		
0.12 In (3.0 Mm)	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 In (0.75 Mm)	1760 (960)	--	°F (°C)	
0.06 In (1.5 Mm)	1760 (960)	--	°F (°C)	
0.12 In (3.0 Mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 In (0.75 Mm)	1290 (700)	--	°F (°C)	
0.06 In (1.5 Mm)	1290 (700)	--	°F (°C)	
0.12 In (3.0 Mm)	1290 (700)	--	°F (°C)	
Oxygen Index	31	--	%	ISO 4589-2



Schulamid 6 MV 14 FR

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	464 to 500 °F	240 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Notes

These are typical property values not to be construed as specification limits.

