

Lucent Pa G6-15

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

15% Glass Fiber Reinforced, Nylon 6

Colors Available

Add "H" for Heat Stabilized

Add "HU" for Weatherable

Typical Properties, Dry as Molded

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.23	1.23 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	14000 psi	96.5 MPa	ASTM D638
Tensile Elongation (Break)	4.0 %	4.0 %	ASTM D638
Flexural Modulus	600000 psi	4140 MPa	ASTM D790
Flexural Strength	21000 psi	145 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	1.1 ft·lb/in	59 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed	370 °F	188 °C	
Peak Melting Temperature	420 to 437 °F	216 to 225 °C	ASTM D789

Notes

These are typical property values not to be construed as specification limits.

