

Lucent Pa 66-01

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

Unreinforced Nylon 66, General Purpose Injection Grade

Colors Available

Add "H" for Heat Stabilized

Add "HU" for Weatherable

Typical Properties, Dry as Molded

General

Features	• General Purpose
Uses	• General Purpose
Appearance	• Colors Available
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	11000 psi	75.8 MPa	ASTM D638
Tensile Elongation (Break)	> 20 %	> 20 %	ASTM D638
Flexural Modulus	410000 psi	2830 MPa	ASTM D790
Flexural Strength	16000 psi	110 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	0.80 ft-lb/in	43 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed	185 °F	85.0 °C	
Peak Melting Temperature	482 to 509 °F	250 to 265 °C	ASTM D789

Notes

These are typical property values not to be construed as specification limits.

