

Schulamid 66 GF 25 H

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

25% glass fiber reinforced, heat stabilized Polyamide 66

General

Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Features	• Heat Aging Resistant	• Medium Viscosity	• Oil Resistant
Automotive Specifications	• FORD WSK-M4D641-A • GM GMP.PA66.083 Color: Black	• GM GMP.PA66.083 Color: Natural • GM QK 003012 H Color: Natural	• IMDS ID 4220736 Color: Natural
UL File Number	• E86615		
Processing Method	• Injection Molding		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.32	--	g/cm ³	ISO 1183/A
Water Absorption				ISO 62
Equilibrium, 73°F (23°C), 50% Rh	1.9	--	%	
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.25E+6 (8600)	798000 (5500)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	23200 (160)	15200 (105)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	7.0	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	3.8 (8.0)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	4.3 (9.0)	6.7 (14)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	24 (50)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	29 (60)	43 (90)	ft·lb/in ² (kJ/m ²)	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	29000 (200)	--	psi (MPa)	ISO 2039-1
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	468 (242)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature	> 482 (> 250)	--	°F (°C)	ISO 306/B50 ISO 306/A50
Ball Pressure Test (248°F (120°C))	Pass	--		IEC 60695-10-2



Schulamid 66 GF 25 H


Polyamide 66
LyondellBasell Industries
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
RTI Elec				UL 746B
0.030 In (0.75 Mm)	248 (120)	--	°F (°C)	
0.06 In (1.5 Mm)	248 (120)	--	°F (°C)	
0.12 In (3.0 Mm)	248 (120)	--	°F (°C)	
RTI Imp				UL 746B
0.030 In (0.75 Mm)	212 (100)	--	°F (°C)	
0.06 In (1.5 Mm)	221 (105)	--	°F (°C)	
0.12 In (3.0 Mm)	239 (115)	--	°F (°C)	
RTI Str				UL 746B
0.030 In (0.75 Mm)	230 (110)	--	°F (°C)	
0.06 In (1.5 Mm)	248 (120)	--	°F (°C)	
0.12 In (3.0 Mm)	266 (130)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Comparative Tracking Index	450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	1.2 (30)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	1.2 (30)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.030 In (0.75 Mm)	HB	--		
0.06 In (1.5 Mm)	HB	--		
0.12 In (3.0 Mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 In (1.5 Mm)	1200 (650)	--	°F (°C)	
0.12 In (3.0 Mm)	1200 (650)	--	°F (°C)	



Schulamid 66 GF 25 H

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

These are typical property values not to be construed as specification limits.

