

Schulamid 66 GF 15 HI

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

15% glass fibre reinforced PA 66, impact modified

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Features	• Impact Modified
Processing Method	• Injection Molding

Physical	Dry	Conditioned	Unit	Test Method
Density	1.20	--	g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	798000 (5500)	464000 (3200)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	16000 (110)	10400 (72.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.6	15	%	ISO 527-2/1A/5
Flexural Modulus ¹	566000 (3900)	--	psi (MPa)	ISO 178
Flexural Stress ¹	21000 (145)	--	psi (MPa)	ISO 178
Flexural Strain at Flexural Strength	6.5	--	%	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	3.8 (8.0)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	7.1 (15)	10 (22)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	26 (55)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	33 (70)	45 (95)	ft·lb/in ² (kJ/m ²)	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	455 (235)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	473 (245)	--	°F (°C)	ISO 306/B50
--	> 482 (> 250)	--	°F (°C)	ISO 306/A50
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index				IEC 60112
0.118 In (3.00 Mm), Solution A	600	--	V	



Schulamid 66 GF 15 HI


Polyamide 66
LyondellBasell Industries
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	0.98 (25)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	0.98 (25)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				
0.06 In (1.5 Mm)	HB	--		IEC 60695-11-10, -20
0.12 In (3.0 Mm)	HB	--		
Glow Wire Flammability Index				
0.06 In (1.5 Mm)	1290 (700)	--	°F (°C)	IEC 60695-2-12
0.12 In (3.0 Mm)	1290 (700)	--	°F (°C)	
Glow Wire Ignition Temperature				
0.06 In (1.5 Mm)	1340 (725)	--	°F (°C)	IEC 60695-2-13
0.12 In (3.0 Mm)	1340 (725)	--	°F (°C)	



Schulamid 66 GF 15 HI

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

