

SCHULAMID® 612 GF 65 H IS

Polyamide 612
Engineering Plastics

Product Description

65% glass fiber reinforced, Polyamide 612 compound, heat stabilized, improved surface finish with very high strength after conditioning

General

Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight		
Features	• Chemical Resistant	• Good Surface Finish	• Heat Aging Resistant
Processing Method	• Gas-Assisted Injection Molding	• Injection Molding	• Water-Assisted Injection Molding

Physical	Dry	Conditioned	Unit	Test Method
Density	1.74	--	g/cm ³	ISO 1183/A
Water Absorption				ISO 62
Equilibrium, 73°F (23°C), 50% RH	0.80	--	%	

Viscosity Number (H ₂ SO ₄ (Sulphuric Acid))	110	--	cm ³ /g	ISO 307
--	-----	----	--------------------	---------

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3.12E+6 (21500)	2.97E+6 (20500)	psi (MPa)	ISO 527-2/1A/1
Tensile Stress (Break)	36300 (250)	31900 (220)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	2.1	2.6	%	ISO 527-2/1A/5
Flexural Modulus ¹ (73°F (23°C))	3.48E+6 (24000)	--	psi (MPa)	ISO 178
Flexural Stress ¹ (2.6% Strain, 73°F (23°C))	62400 (430)	--	psi (MPa)	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°F (-40°C)	6.7 (14)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	7.1 (15)	8.1 (17)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-40°F (-40°C)	No Break	--		
73°F (23°C)	No Break	No Break		

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/Af
264 psi (1.8 MPa), Unannealed	392 (200)	--	°F (°C)	

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1



SCHULAMID® 612 GF 65 H IS

Polyamide 612
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 in (2.00 mm)	< 3.9 (< 100)	--	in/min (mm/min)	ISO 3795
0.0787 in (2.00 mm)	< 3.9 (< 100)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	--		
0.12 in (3.0 mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 in (1.5 mm)	1200 (650)	--	°F (°C)	
0.12 in (3.0 mm)	1200 (650)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.06 in (1.5 mm)	1290 (700)	--	°F (°C)	
0.12 in (3.0 mm)	1290 (700)	--	°F (°C)	


Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications



SCHULAMID® 612 GF 65 H IS

Polyamide 612
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	464 to 536 °F	240 to 280 °C
Mold Temperature	122 to 194 °F	50 to 90 °C

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

