

Matrixx 34N5000

Polybutylene Terephthalate

LyondellBasell Industries

Engineering Plastics

General			
Additive	• Flame Retardant		
Features	• Flame Retardant		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.40	1.40 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8500 psi	58.6 MPa	ASTM D638
Flexural Modulus - Tangent	400000 psi	2760 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.60 ft·lb/in	32 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	320 °F	160 °C	
264 Psi (1.8 Mpa), Unannealed	155 °F	68.3 °C	
RTI Str	170 °F	76.7 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

Notes

These are typical property values not to be construed as specification limits.

