

SCHULADUR[®] A GF 15 HF FR 1

Polybutylene Terephthalate
Engineering Plastics

Product Description

High flow flame retardant halogenated PBT standard grade reinforced with 15% glass fiber; without PBDE

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight		
Features	• Filled • Flame Retardant	• Good Dimensional Stability • Halogenated	• High Flow
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PBT GF15 FR(17)		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.52 g/cm ³	1.52 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	50 cm ³ /10min	50 cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.4 %	1.4 %	
Flow	0.50 %	0.50 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	986000 psi	6800 MPa	ISO 527-2/1A/1
Tensile Stress (Break)	16000 psi	110 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	1.9 ft·lb/in ²	4.0 kJ/m ²	
73°F (23°C)	2.1 ft·lb/in ²	4.5 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	14 ft·lb/in ²	30 kJ/m ²	
73°F (23°C)	16 ft·lb/in ²	34 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	412 °F	211 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	356 °F	180 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	423 °F	217 °C	ISO 306/A50
--	394 °F	201 °C	ISO 306/B50
RTI Elec			UL 746
0.030 in (0.75 mm)	167 °F	75.0 °C	
0.06 in (1.5 mm)	167 °F	75.0 °C	
0.12 in (3.0 mm)	167 °F	75.0 °C	
RTI Imp			UL 746
0.030 in (0.75 mm)	167 °F	75.0 °C	
0.06 in (1.5 mm)	167 °F	75.0 °C	
0.12 in (3.0 mm)	167 °F	75.0 °C	
RTI Str			UL 746
0.030 in (0.75 mm)	167 °F	75.0 °C	
0.06 in (1.5 mm)	167 °F	75.0 °C	
0.12 in (3.0 mm)	167 °F	75.0 °C	





SCHULADUR® A GF 15 HF FR 1

Polybutylene Terephthalate
Engineering Plastics

Electrical	Nominal Value (English)		Nominal Value (SI)		Test Method
Surface Resistivity	> 1.0E+15 ohms		> 1.0E+15 ohms		IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m		> 1.0E+13 ohms·m		IEC 62631-3-1
Comparative Tracking Index	225 V		225 V		IEC 60112
Flammability	Nominal Value (English)		Nominal Value (SI)		Test Method
Flame Rating					UL 94
0.030 in (0.75 mm)		V-0		V-0	IEC 60695-11-10, -20
0.06 in (1.5 mm)	•	V-0	•	V-0	
	•	5VA	•	5VA	
0.12 in (3.0 mm)		V-0		V-0	
Glow Wire Flammability Index					IEC 60695-2-12
0.030 in (0.75 mm)		1760 °F		960 °C	
0.06 in (1.5 mm)		1760 °F		960 °C	
0.12 in (3.0 mm)		1760 °F		960 °C	
Glow Wire Ignition Temperature					IEC 60695-2-13
0.030 in (0.75 mm)		1250 °F		675 °C	
0.06 in (1.5 mm)		1250 °F		675 °C	
0.12 in (3.0 mm)		1250 °F		675 °C	
Oxygen Index		29 %		29 %	ISO 4589-2



SCHULADUR® A GF 15 HF FR 1

Polybutylene Terephthalate
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Suggested Max Regrind	25 %	25 %
Processing (Melt) Temp	482 to 500 °F	250 to 260 °C
Mold Temperature	158 to 194 °F	70 to 90 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Injection Notes

Mould surfaces in contact with melt should be of non-corrosive steel, chrome content >12%

Notes

These are typical property values not to be construed as specification limits.

