

Schuladur A1 GF 30

Polybutylene Terephthalate + PET

LyondellBasell Industries

Engineering Plastics

Product Description

30% glass fibre reinforced PBT/PET-blend

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PBT+PET-GF

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.55 g/cm³	1.55 g/cm³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (260°C/2.16 Kg)	17 cm³/10min	17 cm³/10min	ISO 1133
Water Absorption			ISO 62
Equilibrium, 73°F (23°C), 50% Rh	0.30 %	0.30 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.60E+6 psi	11000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	20600 psi	142 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.1 %	2.1 %	ISO 527-2/1A/5
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.8 ft·lb/in²	8.0 kJ/m²	
73°F (23°C)	3.8 ft·lb/in²	8.0 kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	24 ft·lb/in²	50 kJ/m²	
73°F (23°C)	26 ft·lb/in²	55 kJ/m²	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	38100 psi	263 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	437 °F	225 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	392 °F	200 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	399 °F	204 °C	ISO 306/B50
--	424 °F	218 °C	ISO 306/A50
Ball Pressure Test (392°F (200°C))	Pass	Pass	IEC 60695-10-2
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+16 ohms	> 1.0E+16 ohms	IEC 60093
Volume Resistivity	> 1.0E+12 ohms·m	> 1.0E+12 ohms·m	IEC 62631-3-1
Comparative Tracking Index	300 V	300 V	IEC 60112





Schuladur A1 GF 30

Polybutylene Terephthalate + PET
LyondellBasell Industries
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	1.4 in/min	35 mm/min	ISO 3795
0.0787 In (2.00 Mm)	1.4 in/min	35 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1470 °F	800 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1340 °F	725 °C	
0.12 In (3.0 Mm)	1520 °F	825 °C	
Oxygen Index	19 %	19 %	ISO 4589-2

Additional Information
1.) Not for use in food contact applications
2.) Not for use in medical or pharmaceutical applications

Notes

These are typical property values not to be construed as specification limits.

