

Matrixx 50S5302


Polycarbonate
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.43	1.43 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	16500 psi	114 MPa	ASTM D638
Flexural Modulus	1.00E+6 psi	6890 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.0 ft·lb/in	110 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	305 °F	152 °C	
264 Psi (1.8 Mpa), Unannealed	295 °F	146 °C	
RTI Str	200 °F	93.3 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94



Matrixx 50S5302

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	540 to 590 °F	282 to 310 °C
Middle Temperature	540 to 590 °F	282 to 310 °C
Front Temperature	540 to 590 °F	282 to 310 °C
Processing (Melt) Temp	560 to 610 °F	293 to 321 °C
Mold Temperature	160 to 220 °F	71 to 104 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	40 to 75 rpm	40 to 75 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes
-20°F Dewpoint

Notes

These are typical property values not to be construed as specification limits.

